

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification<sup>6</sup> :

A61K 9/51, 9/14

A1

(11) International Publication Number:

WO 96/25152

(43) International Publication Date:

22 August 1996 (22.08.96)

(21) International Application Number: PCT/US96/01871

(22) International Filing Date: 12 February 1996 (12.02.96)

(30) Priority Data:

08/388,092

14 February 1995 (14.02.95)

US

(71) Applicant: NANOSYSTEMS L.L.C. [US/US]; Building 1,  
1250 South Collegeville Road, Collegeville, PA 19426 (US).(72) Inventors: BOSCH, H., William; 237 Rodney Circle, Bryn  
Mawr, PA 19010 (US). MARCERA, Donna, M.; 122 Poplar  
Court, Collegeville, PA 19426 (US). MUELLER, Ronald,  
L.; 105 Pheasant Way, Downingtown, PA 19335 (US).  
SWANSON, Jon, R.; 310 Brookfield Circle, Macungie, PA  
18062 (US). MISHRA, Dinesh, S.; 102 Springmill Way,  
Harleysville, PA 19438 (US).(74) Agents: WEST, Paul, B.; Ladas & Parry, 26 West 61st Street,  
New York, NY 10023 (US) et al.(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY,  
CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS,  
JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD,  
MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD,  
SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO  
patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ,  
BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH,  
DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE),  
OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR,  
NE, SN, TD, TG).**Published***With international search report.**Before the expiration of the time limit for amending the  
claims and to be republished in the event of the receipt of  
amendments.*

(54) Title: PROCESS OF PREPARING THERAPEUTIC COMPOSITIONS CONTAINING NANOPARTICLES

## (57) Abstract

A process of preparing nanoparticulate drug substances comprising the steps of: preparing a premix of the drug substance and a surface modifier; and subjecting the premix to mechanical means to reduce the particle size of the drug substance, the mechanical means producing shear, impact, cavitation and attrition.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

-1-

**PROCESS OF PREPARING THERAPEUTIC  
COMPOSITIONS CONTAINING NANOPARTICLES**

Field of the Invention

5           This invention relates to a process for preparing therapeutic compositions containing nanoparticles.

Reported Developments

10           Bioavailability is the degree to which a drug becomes available to the target tissue after administration. Many factors can affect bioavailability including the dosage form and various properties, e.g., dissolution rate of the drug. Poor  
15 bioavailability is a significant problem encountered in the development of pharmaceutical compositions, particularly those containing an active ingredient that is poorly soluble in water. Poorly water soluble drugs, i.e., those having a solubility less than about  
20 10 mg/ml, tend to be eliminated from the gastrointestinal tract before being absorbed into the circulation. Moreover, poorly water soluble drugs tend to be unsafe for intravenous administration techniques, which are used primarily in conjunction with fully  
25 soluble drug substances.

          It is known that the rate of dissolution of a particulate drug can increase with increasing surface area, i.e., decreasing particle size. Consequently, methods of making finely divided drugs have been  
30 studied and efforts have been made to control the size and size range of drug particles in pharmaceutical compositions. For example, dry milling techniques have been used to reduce particle size and hence influence drug absorption. However, in conventional dry  
35 milling, as discussed by Lachman et al, *The Theory and Practice of Industrial Pharmacy*, Chapter 2, "Milling", p. 45, (1986), the limit of fineness is reached in the

-2-

region of 100 microns (100,000 nm) when material cakes on the milling chamber. Lachman et al note that wet grinding is beneficial in further reducing particle size, but that flocculation restricts the lower  
5 particle size limit to approximately 10 microns (10,000 nm). However, there tends to be a bias in the pharmaceutical art against wet milling due to concerns associated with contamination. Commercial airjet  
10 milling techniques have provided particles ranging in average particle size from as low as about 1 to 50  $\mu\text{m}$  (1,000 - 50,000 nm). However, such dry milling techniques can cause unacceptable levels of dust.

Other techniques for preparing pharmaceutical compositions include loading drugs into liposomes or  
15 polymers, e.g., during emulsion polymerization. However, such techniques have problems and limitations. For example, a lipid soluble drug is often required in preparing suitable liposomes. Further, unacceptably large amounts of the liposome or polymer are often  
20 required to prepare unit drug doses. Further still, techniques for preparing such pharmaceutical compositions tend to be complex. A principal technical difficulty encountered with emulsion polymerization is the removal of contaminants, such as unreacted monomer  
25 or initiator, which can be toxic, at the end of the manufacturing process.

U.S. Patent 4,540,602 (Motoyama et al) discloses a solid drug pulverized in an aqueous solution of a water-soluble high molecular substance  
30 using a wet grinding machine. However, Motoyama et al teach that as a result of such wet grinding, the drug is formed into finely divided particles ranging from 0.5  $\mu\text{m}$  (500 nm) or less to 5  $\mu\text{m}$  (5,000 nm) in diameter.

EPO 275,796 describes the production of  
35 colloiddally dispersible systems comprising a substance in the form of spherical particles smaller than 500 nm.

-3-

However, the method involves a precipitation effected by mixing a solution of the substance and a miscible non-solvent for the substance and results in the formation of non-crystalline nanoparticles.

5 Furthermore, precipitation techniques for preparing particles tend to provide particles contaminated with solvents. Such solvents are often toxic and can be very difficult, if not impossible, to adequately remove to pharmaceutically acceptable levels to be practical.

10 U.S. Patent 4,107,288 describes particles in the size range from 10 to 1,000 nm containing a biologically or pharmacodynamically active material. However, the particles comprise a crosslinked matrix of macromolecules having the active material supported on  
15 or incorporated into the matrix.

U.S. Patent No. 5,145,684 discloses a process for preparing particles consisting of a crystalline drug substance having a surface modifier or surface active agent adsorbed on the surface of the particles  
20 in an amount sufficient to maintain an average particle size of less than about 400 nanometers. The process of preparation comprises the steps of dispersing the drug substance in a liquid dispersion medium and applying mechanical means in the presence of grinding media to  
25 reduce the particle size of the drug substance to an average particle size of less than 400 nm. The particles can be reduced in the presence of a surface active agent or, alternatively, the particles can be contacted with a surface active agent after attrition.  
30 The presence of the surface active agent prevents flocculation/agglomeration of the nanoparticles.

The mechanical means applied to reduce the particle size of the drug substance is a dispersion mill, the variety of which include a ball mill, an  
35 attrition mill, a vibratory mill and media mill, such as sand mill, and a bead mill.

-4-

The grinding media for the particle size reduction is spherical or particulate in form and includes: ZrO<sub>2</sub> stabilized with magnesia, zirconium silicate, glass, stainless steel, titania, alumina and  
5 ZrO<sub>2</sub> stabilized with yttrium. Processing time of the sample can be several days long. This patent is incorporated herein in its entirety by reference.

To a more limited extent the prior art also utilized microfluidizers for preparing small particle-  
10 size materials in general. Microfluidizers are relatively new devices operating on the submerged jet principle. In operating a microfluidizer to obtain nanoparticulates, a premix flow is forced by a high pressure pump through a so-called interaction chamber  
15 consisting of a system of channels in a ceramic block which split the premix into two streams. Precisely controlled shear, turbulent and cavitation forces are generated within the interaction chamber during microfluidization. The two streams are recombined at  
20 high velocity to produce shear. The so-obtained product can be recycled into the microfluidizer to obtain smaller and smaller particles.

The prior art has reported two distinct advantages of microfluidization over conventional  
25 milling processes (such as reported in U.S. Patent No. 5,145,684, supra): substantial reduction of contamination of the final product, and the ease of production scaleup.

Numerous publications and patents were  
30 devoted to emulsions, liposomes and/or microencapsulated suspensions of various substances including drug substances produced by the use of microfluidizers. See, for example:

1) U.S. Patent No. 5,342,609, directed to  
35 methods of preparing solid apatite particles used in magnetic resonance imaging, x-ray and ultrasound.

-5-

- 2) U.S. Patent No. 5,228,905, directed to producing an oil-in-water dispersion for coating a porous substrate, such as wood.
- 3) U.S. Patent No. 5,039,527 is drawn to a process of producing hexamethylmelamine containing parenteral emulsions.
- 4) G. Gregoriadis, H. Da Silva, and A.T. Florence, "A Procedure for the Efficient Entrapment of Drugs in Dehydration-Rehydration Liposomes (DRVs), "Int. J. Pharm. 65, 235-242 (1990).
- 5) E. Doegito, H. Fessi, M. Appel, F. Puisieux, J. Bolard, and J.P. Devissaguet, "New Techniques for Preparing Submicronic Emulsions -- Application to Amphotericine-B, : STP Pharma Sciences 4, 155-162 (1994).
- 6) D.M. Lidgate, R.C. Fu, N.E. Byars, L.C. Foster, and J.S. Fleitman, "Formulation of Vaccine Adjuvant Muramyl dipeptides. Part 3. Processing Optimization, Characterization and Bioactivity of an Emulsion Vehicle, " Pharm Res. 6, 748-752 (1989).
- 7) H. Talsma, A.Y. Ozer, L. VanBloois, and D.J. Crommelin, "The Size Reduction of Liposomes with a High Pressure Homogenizer (Microfluidizer): Characterization of Prepared Dispersions and Comparison with Conventional Methods," Drug Dev. Ind. Pharm. 15, 197-207 (1989).
- 8) D.M. Lidgate, T. Trattner, R.M. Shultz, and R. Maskiewicz, "Sterile Filtration of a Parenteral Emulsion," Pharm. Res. 9, 860-863 (1990).
- 9) R. Bodmeier, and H. Chen, "Indomethacin Polymeric Nanosuspensions Prepared by Microfluidization," J. Contr. Rel. 12, 223-233 (1990).
- 10) R. Bodmeier, H. Chen, P. Tyle, and P. Jarosz, "Spontaneous Formation of Drug-Containing Acrylic Nanoparticles," J. Microencap, 8, 161-170 (1991).

-6-

11) F. Koosha, and R.H. Muller,  
"Nanoparticle Production by Microfluidization," *Archiv  
Der Pharmazie* 321, 680 (1988).

However, reports are few on reducing mean  
5 particle size (hereinafter sometimes abbreviated as  
MPS) of water-insoluble materials for use in  
pharmaceutical/diagnostic imaging compositions.

The present invention is directed to a  
process incorporating the advantages of microfluidizer  
10 process over conventional milling processes along with  
utilizing formulation and/or process parameters  
necessary for successful particle size reduction of a  
pharmaceutical suspension.

The primary forces attributed to  
15 microfluidization for producing either emulsions or  
dispersions, and for reducing the MPS of water-  
insoluble materials include: shear, involving boundary  
layers, turbulent flow, acceleration and change in flow  
direction; impact, involving collision of solid  
20 elements and collision of particles in the chamber of  
microfluidizer; and cavitation, involving an increased  
change in velocity with a decreased change in pressure  
and turbulent flow. An additional force can be  
attributed to conventional milling processes of  
25 attrition, i.e., grinding by friction. In reference to  
conventional milling process it is understood that the  
process involves the use of gravity, attrition and /or  
media mills, all containing a grinding media.

### 30 Summary Of The Invention

In accordance with the present invention,  
there is provided a process of preparing stable,  
dispersible, water-insoluble, drug nanoparticles  
consisting essentially of a crystalline drug substance  
35 having a surface modifier adsorbed on the surface  
thereof comprising the steps of:



-7-

- a) dispersing a crystalline drug substance in a liquid dispersion medium containing a surface modifier; and
- b) subjecting the liquid dispersion medium to the comminuting action of a microfluidizer asserting shear, impact and cavitation forces onto the crystalline drug substance contained in the liquid dispersion medium for a time necessary to reduce the mean particle size of said crystalline drug substance to less than 400 nm.

The particles can be formulated into pharmaceutical compositions exhibiting remarkably high bioavailability.

This invention also provides a stable dispersion consisting essentially of a liquid dispersion medium and the above-described particles dispersed therein.

In a particularly valuable and important embodiment of the invention, there is provided a pharmaceutical composition comprising the above-described particles and a pharmaceutically acceptable carrier therefor. Such pharmaceutical composition is useful in a method of treating mammals.

It is an advantageous feature that a wide variety of surface modified drug nanoparticles free of unacceptable contamination can be prepared in accordance with this invention.

Still another advantageous feature of this invention is that pharmaceutical compositions containing poorly water soluble drug substances are provided which are suitable for intravenous administration techniques.

#### Detailed Description Of The Invention

This invention is based partly on the discovery that drug particles having an extremely small

-8-

effective average particle size can be prepared by milling in a microfluidizer in conjunction with a surface modifier, and that such particles are stable and do not appreciably flocculate or agglomerate due to interparticle attractive forces and can be formulated into pharmaceutical compositions exhibiting unexpectedly high bioavailability. While the invention is described herein primarily in connection with its preferred utility, i.e., with respect to nanoparticulate drug substances for use in pharmaceutical compositions, it is also believed to be useful in other applications such as the formulation of particulate cosmetic compositions and the preparation of particulate dispersions for use in image and magnetic recording elements.

The particles of this invention comprise a drug substance. The drug substance exists as a discrete, crystalline phase. The crystalline phase differs from a non-crystalline or amorphous phase which results from precipitation techniques, such as described in EPO 275,796 cited above.

#### The Drug Substances

The invention can be practiced with a wide variety of drug substances. The drug substance preferably is present in an essentially pure form. The drug substance must be poorly soluble and dispersible in at least one liquid medium. By "poorly soluble" it is meant that the drug substance has a solubility in the liquid dispersion medium, e.g. water, of less than about 10 mg/ml, and preferably of less than about 1 mg/ml. A preferred liquid dispersion medium is water. However, the invention can be practiced with other liquid media in which a drug substance is poorly soluble and dispersible including, for example, aqueous salt solutions, safflower oil and solvents such as

-9-

ethanol, t-butanol, hexane and glycol. The pH of the aqueous dispersion media can be adjusted by techniques known in the art.

Suitable drug substances can be selected from a variety of known classes of drugs including, for example, analgesics, anti-inflammatory agents, anthelmintics, anti-arrhythmic agents, antibiotics (including penicillins), anticoagulants, antidepressants, antidiabetic agents, antiepileptics, antihistamines, antihypertensive agents, antimuscarinic agents, antimycobacterial agents, antineoplastic agents, immunosuppressants, antithyroid agents, antiviral agents, anxiolytic sedatives (hypnotics and neuroleptics), astringents, beta-adrenoceptor blocking agents, blood products and substitutes, cardiac inotropic agents, corticosteroids, cough suppressants (expectorants and mucolytics), diagnostic agents, diuretics, dopaminergics (antiparkinsonian agents), haemostatics, immunological agents, lipid regulating agents, muscle relaxants, parasympathomimetics, parathyroid calcitonin and biphosphonates, prostaglandins, radio-pharmaceuticals, sex hormones (including steroids), anti-allergic agents, stimulants and anoretics, sympathomimetics, thyroid agents, vasodilators and xanthines. Preferred drug substances include those intended for oral administration and intravenous administration. A description of these classes of drugs and a listing of species within each class can be found in Martindale, *The Extra Pharmacopoeia*, Twenty-ninth Edition, The Pharmaceutical Press, London, 1989, the disclosure of which is hereby incorporated herein by reference in its entirety. The drug substances are commercially available and/or can be prepared by techniques known in the art.

-10-

Representative illustrative species of drug substances useful in the practice of this invention include:

- 17-a-pregno-2,4-dien-20-yno-[2,3-d]-isoxazol-17-ol  
5 (Danazol);  
5a,17a,-1'-(methylsulfonyl)-1'H-pregn-20-yno[3,2-c]-pyrazol-17-ol (Steroid A);  
piposulfam;  
piposulfan;  
10 camptothecin; and  
ethyl-3,5-diacetoamido-2,4-6-triiodobenzoate.

In particularly preferred embodiments of the invention, the drug substance is a steroid such as danazol or Steroid A or an antiviral agent.

15

#### Surface Modifiers

- The particles of this invention contain a discrete phase of a drug substance as described above having a surface modifier adsorbed on the surface  
20 thereof. Useful surface modifiers are believed to include those which physically adhere to the surface of the drug substance but do not chemically bond to the drug.

- Suitable surface modifiers can preferably be  
25 selected from known organic and inorganic pharmaceutical excipients. Such excipients include various polymers, low molecular weight oligomers, natural products and surfactants. Preferred surface modifiers include nonionic and anionic surfactants.  
30 Representative examples of excipients include gelatin, casein, lecithin (phosphatides), gum acacia, cholesterol, tragacanth, stearic acid, benzalkonium chloride, calcium stearate, glyceryl monostearate, cetostearyl alcohol, cetomacrogol emulsifying wax,  
35 sorbitan esters, polyoxyethylene alkyl ethers, e.g., macrogol ethers such as cetomacrogol 1000,

-11-

polyoxyethylene castor oil derivatives, polyoxyethylene sorbitan fatty acid esters, e.g., the commercially available Tweens, polyethylene glycols, polyoxyethylene stearates, colloidal silicon dioxide, phosphates, sodium dodecylsulfate, carboxymethylcellulose calcium, carboxymethylcellulose sodium, methylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, hydroxypropylmethylcellulose phthalate, noncrystalline cellulose, magnesium aluminum silicate, triethanolamine, polyvinyl alcohol (PVA), and polyvinylpyrrolidone (PVP). Most of these excipients are described in detail in the *Handbook of Pharmaceutical Excipients*, published jointly by the American Pharmaceutical Association and The Pharmaceutical Society of Great Britain, the Pharmaceutical Press, 1986. The surface modifiers are commercially available and/or can be prepared by techniques known in the art. Two or more surface modifiers can be used in combination.

Particularly preferred surface modifiers include polyvinyl pyrrolidone, Pluronic F68 and F108, which are block copolymers of ethylene oxide and propylene oxide, Tetronic 908, which is a tetrafunctional block copolymer derived from sequential addition of ethylene oxide and propylene oxide to ethylenediamine, dextran, lecithin, Aerosol OT, which is a dioctyl ester of sodium sulfosuccinic acid, available from American Cyanamid, Duponol P, which is a sodium lauryl sulfate, available from DuPont, Triton X-200, which is an alkyl aryl polyether sulfonate, available from Rohm and Haas, Tween 80, which is a polyoxyethylene sorbitan fatty acid ester, available from ICI Specialty Chemicals, Carbowax 3350 and 934, which are polyethylene glycols available from Union Carbide. Surface modifiers which have found to be

-12-

particularly useful include polyvinylpyrrolidone, Pluronic F-68, and lecithin.

The surface modifier is adsorbed on the surface of the drug substance in an amount sufficient  
5 to maintain an effective average particle size of less than about 400 nm. The surface modifier does not chemically react with the drug substance or itself. Furthermore, the individually adsorbed molecules of the surface modifier are essentially free of intermolecular  
10 crosslinkages.

As used herein, particle size refers to a number average particle size of less than about 400 nm as measured by conventional particle size measuring techniques well known to those skilled in the art, such  
15 as sedimentation field flow fractionation, photon correlation spectroscopy, or disk centrifugation. By "effective average particle size of less than about 400 nm" it is meant that at least 90% of the particles have a weight average particle size of less than about 400  
20 nm when measured by the above-noted techniques. In preferred embodiments of the invention, the effective average particle size is less than about 250 nm. In some embodiments of the invention, an effective average particle size of less than about 100 nm has been  
25 achieved. With reference to the effective average particle size, it is preferred that at least 95% and, more preferably, at least 99% of the particles have a particle size less than the effective average, e.g., 400 nm. In particularly preferred embodiments,  
30 essentially all of the particles have a size less than 400 nm.

#### The Microfluidizer

In the practice of the present invention the  
35 following microfluidizers were used, all supplied by Microfluidics International Corporation:

-13-

Model M110-EH, which is a laboratory scale microfluidizer which utilizes an electric hydraulic pump;

5 Model M-110Y, which is a laboratory scale microfluidizer equipped with a sanitary pressure transducer connected to a digital data acquisition system;

10 Model M-140K, which is a high pressure microfluidizer with a pressure limit of 40,000 psi; and

Model M-210, which is a pilot plant microfluidizer with a pressure range from 3,000 to 30,000 psi, and with flow rates between 1.9 to 5.7 L/min. It is capable of handling a sample size of 3.8 L or greater.

15 As indicated, the primary forces attributed to microfluidization by the microfluidizer for producing either emulsions or dispersions, and for reducing mean particle size of water-insoluble materials are:

20 shear, involving boundary layers, turbulent flow, acceleration and change in flow direction;

impact, involving collision of the particles processed with solid elements of the microfluidizer, and collision between the particles being processed;

25 and

cavitation, involving an increased change in velocity with a decreased change in pressure, and turbulent flow.

30 An additional force can be attributed to attrition, i.e., grinding by friction.

The M-110Y laboratory scale microfluidizer consists of an air motor connected to a hydraulic pump which circulates the process fluid. The formulation stream is propelled at high pressures (up to 23,000 psi) through a specially designed interaction chamber

35 which has fixed microchannels that focus the

-14-

formulation stream and accelerate it to a high velocity. Within the chamber the formulation is subjected to intense shear, impact and cavitation, all of which contribute to particle size reduction. After  
5 processing, the formulation stream is passed through a heat exchanger coil and can be collected or recirculated through the machine. The microfluidizer was typically used in a continuous processing mode for up to three hour of total processing time. The heat  
10 exchanger and interaction chamber were externally cooled with a refrigerated circulating water bath.

The use of microfluidization in pharmaceutical dosage form development has largely been limited to processing of emulsions or liposomes as  
15 previously discussed.

#### The Process of Making the Nanoparticulates

A general procedure for preparing the particles useful in the practice of this invention  
20 follows. The drug selected is obtained commercially and/or prepared by techniques known in the art in a conventional coarse form. It is preferred, but not essential, that the particle size of the coarse drug substance selected be less than about 100  $\mu\text{m}$ , as  
25 determined by sieve analysis. If the coarse particle size of the drug substance is greater than about 100  $\mu\text{m}$  then it is preferred that the coarse particles of the drug substance be reduced in size to less than 100  $\mu\text{m}$  using a conventional milling method such as airjet or  
30 fragmentation milling.

The coarse drug substance selected can then be added to a liquid medium in which it is essentially insoluble to form a premix. The concentration of the drug substance in the liquid medium can vary from about  
35 0.1 - 60% w/w, and preferably is from 5 - 30% (w/w). It is preferred, but not essential, that the surface



-15-

modifier be present in the premix. The concentration of the surface modifier can vary from about 0.1 to 90%, and preferably is 1 - 75%, more preferably 20 - 60%, by weight based on the total combined weight of the drug substance and surface modifier. The apparent viscosity of the premix suspension is preferably less than about 1000 centipoise.

The premix then can be transferred to the microfluidizer and circulated continuously first at low pressures, then at maximum capacity having a fluid pressure of from about 3,000 to 30,000 psi until the desired particle size reduction is achieved. The particles must be reduced in size at a temperature which does not significantly degrade the drug substance. Processing temperatures of less than about 30 - 40° C are preferred.

There are two methods to collect a slurry and re-pass it in a microfluidizer. The "discreet pass" method collects every pass through the microfluidizer until all of the slurry has been passed through before re-introducing it again to the microfluidizer. This guarantees that every substance or particle has "seen" the interaction chamber the same amount of times. The second method recirculates the slurry by collecting it in a receiving tank and allowing the entire mixture to randomly mix and pass through the interaction chamber. We have found that recirculating a slurry is just as effective as the "discreet pass" method, however, maintaining slurry homogeneity in the receiving tank is important.

The surface modifier, if it was not present in the premix, must be added to the dispersion after attrition in an amount as described for the premix above. Thereafter, the dispersion can be mixed, e.g., by shaking vigorously. Optionally, the dispersion can be subjected to a sonication step, e.g., using an

-16-

ultrasonic power supply. For example, the dispersion can be subjected to ultrasonic energy having a frequency of 20 - 80 kHz for a time of about 1 to 120 seconds.

5           The relative amount of drug substance and surface modifier can vary widely and the optimal amount of the surface modifier can depend, for example, upon the particular drug substance and surface modifier selected, the critical micelle concentration of the  
10 surface modifier if it forms micelles, etc. The surface modifier preferably is present in an amount of about 0.1-10 mg per square meter surface area of the drug substance. The surface modifier can be present in an amount of 0.1-90%, preferably 20-60% by weight based  
15 on the total weight of the dry particle.

The resulting dispersion of this invention is stable and consists of the liquid dispersion medium and the above-described particles. The dispersion of surface modified drug nanoparticles can be spray coated  
20 onto sugar spheres or onto a pharmaceutical excipient in a fluid-bed spray coater by techniques well known in the art.

Pharmaceutical compositions according to this invention include the particles described above and a  
25 pharmaceutically acceptable carrier therefor. Suitable pharmaceutically acceptable carriers are well known to those skilled in the art. These include non-toxic physiologically acceptable carriers, adjuvants or vehicles for parenteral injection, for oral  
30 administration in solid or liquid form, for rectal administration, and the like. A method of treating a mammal in accordance with this invention comprises the step of administering to the mammal in need of treatment an effective amount of the above-described  
35 pharmaceutical composition. The selected dosage level of the drug substance for treatment is effective to

-17-

obtain a desired therapeutic response for a particular composition and method of administration. The selected dosage level therefore, depends upon the particular drug substance, the desired therapeutic effect, on the route of administration, on the desired duration of treatment and other factors. As noted, it is a particularly advantageous feature that the pharmaceutical compositions of this invention exhibit unexpectedly high bioavailability as illustrated in the examples which follow. Furthermore, it is contemplated that the drug particles of this invention provide more rapid onset of drug action in oral applications and decreased gastric irritancy.

It is contemplated that the pharmaceutical compositions of this invention will be particularly useful in oral and parenteral, including intravenous, administration applications. It is expected that poorly water soluble drug substances, which prior to this invention, could not have been administered intravenously, may be administered safely in accordance with this invention. Additionally, drug substances which could not have been administered orally due to poor bioavailability may be effectively administered in accordance with this invention.

While applicants do not wish to be bound by theoretical mechanisms, it is believed that the surface modifier hinders the flocculation and/or agglomeration of the particles by functioning as a mechanical or steric barrier between the particles, minimizing the close, interparticle approach necessary for agglomeration and flocculation. Alternatively, if the surface modifier has ionic groups, stabilization by electrostatic repulsion may result. It was surprising that stable drug particles of such a small effective average particle size and free of unacceptable

-18-

contamination could be prepared by the method of this invention.

Illustrative examples of drug substance microfluidized in the presence of surface active agents and mean particle size of the microfluidized drug substances are shown in Table I.

TABLE I  
Microfluidization of Therapeutics

Compound % w/w	Surfactant % w/w	Mean Particle Size
naproxen (2.5%)	HPMC (0.25%)	309 nm (30 min) 301 nm (60 min)
naproxen (2.5%)	HPMC (1.75%)	335 nm (30 min) 307 nm (60 min)
naproxen (20%)	HPMC (2.0%)	314 nm (180 min)
naproxen (20%)	HPC (1.6%)	223 nm (180 min)
naproxen (40%)	PVP K-29/32 (6%)	271 nm (150 min)
WIN 49596 (20%)	SLS (0.2%)	224 nm (60 min)
WIN 63394 (6.8%)	F68 (5%)	284 nm (30 min)
Danazol (12%)	DOSS (0.3%)	318 nm (180 min)

wherein

naproxen = 6 methoxy- $\alpha$ -methyl-2-naphthaleneacetic acid

HPMC = hydroxypropylmethylcellulose

15 HPC = hydroxypropylcellulose

WIN 49596 = (5- $\alpha$ -, 17- $\alpha$ )-1'-(methylsulfonyl)-1'-H-preg-20-yno[3,2-C]pyrazol-17-ol

(generic name zanoterone)

20 WIN 63394 = Benzoic acid, 6-dichloro-[6-methoxy-4-(1-methylethyl)-3-oxo-1,2-benzisothiazol-2-(3H)-yl]methyl S,S, dioxide

SLS = sodium lauryl sulfate

-19-

DOSS = sodium dioctylsulfosuccinate

The invention has been described in detail  
with particular reference to certain preferred  
5 embodiments thereof, but it will be understood that  
variations and modifications can be effected within the  
spirit and scope of the invention.

-20-

What Is Claimed Is:

1. A process for preparing particles  
consisting essentially of 99.9 - 10% by weight of a  
5 crystalline drug substance having a solubility in water  
of less than 10 mg/ml, said drug substance having a  
non-crosslinked surface modifier adsorbed on the  
surface thereof in an amount of 0.1 - 90% by weight and  
sufficient to maintain an effective average particle  
10 size of less than about 400 nm, said process comprises  
the steps of:

preparing a premix of said crystalline drug  
substance and said surface modifier by mixing them; and  
15

subjecting said premix to mechanical means to  
reduce the particle size thereof to less than 400 nm by  
the action of said mechanical means which produces  
shear, impact, cavitation and attrition.  
20

2. The process of claim 1 wherein said  
particles have an effective particle size of less than  
250 nm.

25 3. The process of claim 1 wherein said  
particles have an effective particle size of less than  
100 nm.

4. The process of claim 1 wherein said drug  
30 substance is selected from the group consisting of:  
analgesics, anti-inflammatory agents, anthelmintics,  
anti-arrhythmic agents, antibiotics, anticoagulants,  
antidepressants, antidiabetic agents, antiepileptics,  
antihistamines, antihypertensive agents, antimuscarinic  
35 agents, antimycobacterial agents, antineoplastic  
agents, immunosuppressants, antithyroid agents,

-21-

antiviral agents, anxiolytic sedatives, astringents, beta-adrenoceptor blocking agents, contrast media, corticosteroids, cough suppressants, diuretics, dopaminergics, haemostatics, immuriological agents, 5 lipid regulating agents, muscle relaxants, parasympathomimetics, parathyroid calcitonin, prostaglandins, radio-pharmaceuticals, sex hormones, anti-allergic agents, stimulants, sympathomimetics, thyroid agents, vasodilators and xanthines.

10

5. The process of claim 1 wherein said drug substance is a steroid.

6. The process of claim 1 wherein said said 15 drug substance is selected from the group consisting of: (Danazol), 5a,17a,-1'-(methylsulfonyl)-1'H-pregn-20-yno[3,2-c]-pyrazol-17-ol, piposulfam, piposulfan, camptothecin and ethyl-3,5-diacetoamido-2,4-6-triiodobenzoate.

20

7. The process of claim 1 wherein said surface modifier is selected from the group consisting of: gelatin, casein, lecithin, gum acacia, cholesterol, tragacanth, stearic acid, benzalkonium 25 chloride, calcium stearate, glyceryl monostearate, cetostearyl alcohol, cetomacrogol emulsifying wax, sorbitan esters, polyoxyethylene alkyl ethers, polyoxyethylene caster oil derivatives, polyoxyethylene sorbitan fatty acid esters, polyethylene glycols, 30 polyoxyethylene stearates, colloidol silicon dioxide, phosphates, sodium dodecylsulfate, carboxymethylcellulose calcium, carboxymethylcellulose sodium, methylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, hydroxypropylmethycellulose 35 phthalate, noncrystalline cellulose, magnesium aluminum

-22-

silicate, triethanolamine, polyvinyl alcohol, and polyvinylpyrrolidone.

8. The process of claim 1 wherein said  
5 surface modifier is selected from the group consisting of: an ethylene oxide-propylene oxide block copolymer, lecithin, an alkyl aryl polyether sulfonate, gum acacia, sodium dodecylsulfate, and a dioctylester of sodium sulfosuccinic acid.

10

9. A stable dispersion consisting essentially of a liquid dispersion medium and the particles of claim 1.

15

10. The dispersion of claim 9 wherein said dispersion medium is water.

11. The dispersion of claim 9 wherein said dispersion medium is selected from the group consisting  
20 of safflower oil, ethanol, t-butanol, hexane and glycol.

12. A pharmaceutical composition comprising the particles prepared by the process of claim 1 in a  
25 pharmaceutically acceptable carrier.

13. A method of treating a mammal comprising the step of administering to the mammal an effective amount of the pharmaceutical composition of claim 12.

30



# INTERNATIONAL SEARCH REPORT

Int. Patent Application No.  
PCT/US 96/01871

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61K9/51 A61K9/14

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 499 299 (STERLING WINTHROP) 19 August 1992 cited in the application see the whole document	1-13
Y	--- JOURNAL OF CONTROLLED RELEASE, vol. 12, no. 3, May 1990, AMSTERDAM NL, pages 223-233, XP000132663 ROLAND BODMEIER ET AL.: "Indomethacin polymeric nanosuspensions prepared by microfluidization" see the whole document -----	1-13

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*A\* document member of the same patent family

Date of the actual completion of the international search

6 June 1996

Date of mailing of the international search report

21.06.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Ventura Amat, A

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/01871

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-499299	19-08-92	US-A- 5145684	08-09-92
		AU-B- 642066	07-10-93
		AU-B- 1014592	30-07-92
		AU-B- 654836	24-11-94
		AU-B- 1014792	30-07-92
		EP-A- 0498482	12-08-92
		IL-A- 100755	08-12-95
		JP-A- 4317053	09-11-92
		JP-A- 4295420	20-10-92
		US-A- 5451393	19-09-95
		US-A- 5494683	27-02-96
		US-A- 5399363	21-03-95
		US-A- 5318767	07-06-94
-----			